

#### **Product Bulletin**

Product Name: Micron MC-900 PT. 2 Product Code: 2202905 Revision Date: March 18, 2024

# Micron MC-900 PT. 2

#### Micron Zinc Replenisher

Micron MC-900 phosphate coating system is a lubrication grade process for steel. Provides extrusion and metal drawing aid. Typical coating weights of 600-1200 mg/ft2. Provides typically darker coatings then conventional products and a preferred denser sludge by-product for less dusting on coils and less waste volume.

Micron MC-900 is a two part system (Make-up # M C 900 & Replenisher MC-900) that provides a micro crystalline, tightly bonded coating on steel. A zero iron operating system with a unique coating structure for better lubrication.

Part #1 is used to make up a bath @6-8% vol. Part #2 is used to replenish and run bath.

#### **Features & Benefits**

- Lowest use cost.
- No dump operating system.
- Can be used in coil coating, barrel slug processes, immersion or spray.
- Reduced sludging and scale build-up on equipment.
- Bonds lubricant coatings tighter and more uniform.
- Can be used with all conventional and advanced lubricant coatings.
- Provides wide coating range as required: 500-1200 mg/sq.ft.

### **Physical Data**

pН	< 1.0
Product Type	Liquid
Spec. Gravity	1.52
lbs./gal.	12.68
Foam, 0 = Low, 9 = High	0
Shelf-Life Years	10 Years
Freeze Information	Not damaged by freezing

# **Typical Processing**

- 1. Pre-clean as required with acid pickling and/or alkaline cleaning
- 2. Rinse
- 3. Rinse









#### **Product Bulletin**

Product Name: Micron MC-900 PT. 2 Product Code: 2202905 Revision Date: March 18, 2024

- Phosphate coat: MICRON MC-900 (Make-up & Replenisher) Use 7%~ of MAKE-UP = 21 points total acid "Part #1" to prepare a new bath. 1% PART #2 REPLENISHER = 4 POINTS TOTAL ACID.
- 5. Rinse
- 6. Hot rinse, 150 F., 30-60 sec., neutralized to ph of 9~ (w/240-L or #856L)
- 7. Lubricant coat: LOC-LUBE, POLY-LUBE, LIME, OIL ETC.

# **Packaging**

	<del>-</del>
Container Type	Poly
Net Units	700
Tare Wt.	25
Gross Wt.	725
DOT_Name	UN 3264, Corrosive Liquid, Acidic, inorganic, N.O.S., (Phosphoric & Nitric Acids),8, PG II
DOT Hazard	Corrosive
Tarriff ID	

#### **Use Parameters**

Concentration Range	20-30 Points total acid.( = 6-10%)
Temperature Range	175 – 190 deg F
Time Range	4 – 10 min
Agitation	N/A

# **Waste Disposal**

Treat for metals, acids.

# **Holding Tank Materials of Construction**

Acid resistant. Steel, stainless or poly.

### Other Information

It is important that the OSHA DATA, "Material Safety Data Sheet" be carefully read and reviewed with the users of this product. OSHA data is required to be posted in the work area by law.





#### **Product Bulletin**

Product Name: Micron MC-900 PT. 2 Product Code: 2202905 Revision Date: March 18, 2024

WARRANTY: HUBBARD-HALL INC. IS NOT RESPONSIBLE FOR THE MISUSE, MISAPPLICATION, OR MISHANDLING OF THIS PRODUCT. SEE THE TERMS AND CONDITIONS OF SALE ON OUR WEBSITE FOR ADDITIONAL TERMS AND CONCERNING OUR PRODUCTS, INCLUDING BUT NOT LIMITED TO, LIMITATIONS AND DISCLAIMERS OF WARRANTIES AND LIABILITIES.

### **Our People. Your Problem Solvers.**

For more information on this process, please call us at 203.756.5521 or email: <a href="techservice@hubbardhall.com">techservice@hubbardhall.com</a>

Hubbard-Hall holds certifications for **ISO 9001:2015**, Responsible Distribution, as accredited by the **ACD** (Alliance for Chemical Distributors) and as a **Women-Owned Small Business**, as well as maintaining an association with **Omni-Chem**<sup>136</sup>.

